

AD-A058 372

PENNSYLVANIA UNIV PHILADELPHIA LAB FOR RESEARCH ON --ETC F/G 7/4
POLYACETYLENE, (CH) SUB X:N-TYPE AND P-TYPE DOPING AND COMPENSA--ETC(U)
AUG 78 C K CHIANG, S C GAU, C R FINCHER N00014-75-C-0962

UNCLASSIFIED

LRSN-TR-78-4

NL

1 OF 1
AD
A058 372

1



Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

LEVEL II**(12)**

REPORT DOCUMENTATION PAGE

READ INSTRUCTIONS
BEFORE COMPLETING FORM

1. REPORT NUMBER Technical Report No. 78-4	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Polyacetylene, (CH) _x ; n-Type and p-Type Doping and Compensation		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) C. K. Chiang, [†] S.C. Gau, C. R. Fincher, Jr., [†] Y. W. Park, [†] A. G. MacDiarmid, and A. J. Heeger [†]		8. CONTRACT OR GRANT NUMBER(s) N00014-75-C-0962 ✓
9. PERFORMING ORGANIZATION NAME AND ADDRESS Departments of Chemistry and [†] Physics and the Laboratory for Research on the Structure of Matter, University of Pennsylvania, Philadelphia, PA 19104		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR-356-602
11. CONTROLLING OFFICE NAME AND ADDRESS Department of the Navy Office of Naval Research Arlington, Virginia 22217		12. REPORT DATE August 4, 1978 ✓
		13. NUMBER OF PAGES 14
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

Distribution unlimited; approved for public release

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

DDC**SEP 7 1978****E**

18. SUPPLEMENTARY NOTES

Published in Appl. Phys. Lett., 33, 18 (1978).

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Polyacetylene, (CH)_x; n-type doping; p-type doping; compensation; donors; acceptors; p-n junctions; semiconductor device application; crystalline films; covalent polymer; electronic properties; doping techniques; Na-doped films; sodium naphthalides; electron transfer; ionic impurities; compensated polymer; charge transfer; polycation; polymer chains; band gap; bound states; electronic (over

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

A series of experiments are reported which demonstrate that donors or acceptors can dope polyacetylene to n-type or p-type respectively, and that the two kinds of dopants can compensate one another. The formation of a rectifying p-n junction is demonstrated. The results suggest the possibility of utilizing doped polyacetylene in a variety of potential semiconductor device applications.

DD FORM 1473
AN 73EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

AD No. **ADA058372**
DDC FILE COPY

19. (Cont'd)

carriers; thermoelectric power; Seebeck coefficient; diode characteristic;
I-V curve; optical studies; solar spectrum.

VDV028325

000 LIFE C06A

000

SEP 7 1954
D D C
RECEIVED
F

OFFICE OF NAVAL RESEARCH

Contract ¹³ N00014-75-C-0962

Task No. 356-602

TECHNICAL REPORT NO. 78-4

⁶ Polyacetylene, (CH)_x n-Type and p-Type Doping and Compensation ,

by

¹⁰ C. K. Chiang, S. C. Gau, C. R. Fincher, Jr., Y. W. Park,

A. G. MacDiarmid, and A. J. Heeger

Published in

Appl. Phys. Lett., 33, 18 (1978)

Department of Chemistry and
†Department of Physics,
Laboratory for Research on the Structure of Matter,
University of Pennsylvania,
Philadelphia, PA 19104

August 4, 1978

Reproduction in whole or in part is permitted for
any purpose of the United States Government

Approved for public release; distribution unlimited.

¹⁴ LRSM-TR-78-4

⁹ Interim technical rept's

78 08 24 03 9

279 025

alt

Polyacetylene, $(CH)_x$: n-Type and p-Type Doping and Compensation

C. K. Chiang[†], S. C. Gau[‡], C. R. Fincher, Jr.[†], Y. W. Park[†],
A. G. MacDiarmid[‡], and A. J. Heeger[†]

Laboratory for Research on the Structure of Matter
University of Pennsylvania
Philadelphia, PA 19104

Abstract

A series of experiments are reported which demonstrate that donors or acceptors can dope polyacetylene to n-type or p-type respectively, and that the two kinds of dopants can compensate one another. The formation of a rectifying p-n junction is demonstrated. These results suggest the possibility of utilizing doped polyacetylene in a variety of potential semiconductor device applications.

[†] Department of Physics
University of Pennsylvania

[‡] Department of Chemistry
University of Pennsylvania

ACCESSION for	
NTIS	White Section <input checked="" type="checkbox"/>
DOC	Buff Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

78 08 24 03 9

We have recently reported that when flexible, crystalline films of the covalent polymer, polyacetylene, $(CH)_x$, are doped, their conductivity can be systematically and controllably varied over a range of more than eleven orders of magnitude.¹⁻³ The most highly conducting films exhibited a conductivity at room temperature of order $10^3 \text{ ohm}^{-1} \cdot \text{cm}^{-1}$, by far the highest observed for any covalent organic polymer. The electronic properties are similar to those of a simple classical semiconductor with thermally activated conductivity at low dopant levels and a transition to metallic properties at high levels.² The dopant can be either an acceptor such as bromine, iodine or AsF_5 ;^{1, 2} or the dopant can be a donor such as lithium, sodium and potassium.^{3, 4} We report in this paper on a series of experiments which demonstrate that both donors and acceptors can dope polyacetylene to n-type or p-type material respectively, and that the two kinds of dopants can compensate one another. The demonstration of successful n-type and p-type doping together with compensation indicates the possibility of utilizing doped polyacetylene in a variety of potential semiconductor device applications.

The $(CH)_x$ polymer films were prepared using refinements of the techniques developed by Shirakawa et al.⁵ The doping techniques were developed recently in our laboratories. Details on the preparation and doping are published elsewhere.^{1, 3, 4}

When pure polyacetylene is doped with an acceptor, the electrical conductivity increases sharply over many orders of magnitude at low

concentration, then saturates at higher dopant levels, above approximately 1%.²⁻⁴ The maximum conductivity we have reported to date at room temperature was $560 \Omega^{-1} \text{ cm}^{-1}$ for $\text{cis}[\text{CH}(\text{AsF}_6)_{0.14}]_x$.^{2,3} Donor doping leads to qualitatively similar results. The highest conductivity obtained thus far through donor doping was $200 \Omega^{-1} \text{ cm}^{-1}$.⁴ The typical behavior for the electrical conductivity as a function of dopant concentration is shown in Figure 1. The general features appear to be the same for the various donor and acceptor dopants, but with detailed differences in the saturation values and the critical concentration for the metal-insulator transition.

Earlier studies^{2,3} suggested that compensation could be achieved. The sensitivity of $(\text{CH})_x$ to impurities implies that the residual conductivity in "pure" $(\text{CH})_x$ is probably due to residual impurities or defects at very low levels. Exposure of pure $(\text{CH})_x$ to vapor of the donor, NH_3 , causes the conductivity of trans- $(\text{CH})_x$ to fall more than four orders of magnitude without detectable weight increase. The exposure to NH_3 thus results in compensation of the residual impurities and/or defects.

Compensation of n-type material by subsequent acceptor doping has been successfully demonstrated using Na (donor) and iodine or AsF_6 (acceptors). Figures 2 and 3 show the compensation of Na-doped polyacetylene by iodine and AsF_6 , respectively. The Na-doped films were prepared by treating the polymers with a solution of sodium naphthalide,³ $\text{Na}^+(\text{C}_{10}\text{H}_8)$, in THF whereupon electron transfer from the naphthalide

radical anion to the $(\text{CH})_x$ occurred. In each case the pure cis-polyacetylene was first doped with sodium until the conductivity was in the saturation range. Subsequent exposure to iodine or AsF_5 vapor resulted in the compensation curves plotted in Figs. 2 and 3. The compensation proceeds more slowly than the original doping; the electrical conductivity of the n-type sample gradually decreases and reaches a minimum. Continued doping with iodine or AsF_5 results in conversion to p-type material with an associated increase in conductivity.

Due to the relatively high concentration of ionic impurities in the sample, the conductivity of the fully compensated sample (at minimum) remained higher than that of the original polymer prior to doping. Nevertheless Figures 2 and 3 show compensation over approximately four orders of magnitude starting from the highest doping levels where the samples are metallic. Even more precise compensation can be expected using intermediate to low initial doping.

Starting with an initial composition $(\text{CHNa}_{0.27})_x$, the compensation point with iodine occurred at $(\text{CHNa}_{0.27}\text{I}_{0.28})_x$; all compositions being determined by measurement of weight increase. Thus the compensation point corresponds approximately to a stoichiometric sodium to iodine ratio consistent (within the limits of error) to the presence of equal concentrations of Na^+ and I^- in the compensated polymer. Continued doping leads to p-type material, where the iodine is known to be present as I_3^- from Raman studies.^{6,7}

From these observations, the overall shape of the compensation curves, and the fact that the doping can be removed chemically,⁴ we believe the doping results from charge transfer, and the compensation is best viewed as of direct chemical origin. Charge transfer occurs from polymer to acceptor (A) with the polymer chain acting as a polycation in the presence of an A^- species (in the case of iodine, the compensation and Raman experiments suggest I^- in the presence of excess Na^+ going over to I_3^- in the p-type material). For a donor (D), the polymer chains act as a polyanion in the presence of the D^+ species. The charge transfer need not be complete. The resulting electron (or hole) on the polymer chain is weakly bound to the D^+ (or A^-) ions by the Coulomb potential, forming donor (or acceptor) states in the gap. At low levels, thermal activation out of the bound states results in carriers for transport along the polymer chain. Above approximately 1 mole% doping, the bound states are screened, and the carriers are free to move along the polymer chains resulting in metallic behavior.² Compensation at least in the case of iodine evidently occurs through formation of (D^+A^-) leaving the polymer chain essentially neutral and without electronic carriers.

The assignment of donor doped material as n-type and acceptor doped material as p-type follows from the chemical properties of the donor and acceptor dopants. Moreover, the assignments are consistent with the results obtained from studies of graphite intercalated with alkali

metals and iodine or AsF_6 respectively.⁸ Finally thermoelectric power measurements on acceptor doped $(\text{CH})_x$ yield a positive Seebeck coefficient consistent with p-type material. Moreover, the value of $+15 \mu\text{V/K}$ found at room temperature for $(\text{CH})_x$ heavily doped with AsF_6 is consistent with metallic behavior. Initial experiments directed toward fabrication of p-n junctions are encouraging as shown in Fig. 4. The junction was made by mechanically pressing together n-type (Na-doped) and p-type (AsF_6 -doped) strips of polymer film. Although some hysteresis is evident, a typical diode characteristic is seen in the I-V curve. Junctions have also been made using a single polymer strip doped n-type on one-half and p-type on the other half. Note that in all cases the forward bias direction was consistent with the p-type and n-type character of the acceptor and donor doped material.

In summary, polyacetylene exhibits many attractive features for potential device applications. From optical studies,⁹ we conclude that the intrinsic band gap is at approximately 1.6 eV; i. e. reasonably well matched to the solar spectrum. In addition to the ability to dope to n-type or p-type and to compensate, the chemical and mechanical properties are attractive. The material can be synthesized in the form of strong, flexible, free-standing films or as films on glass or metal substrates.

Considering possible polyacetylene derivatives, replacement of some or all of the hydrogen atoms in $(\text{CH})_x$ with organic or inorganic

groups, copolymerization of acetylene with other acetylenes or olefins and the use of different dopants, this large new class of organic polymer semiconductors offer the possibility of unique chemical tuning of electrical properties.

Acknowledgement: This work was supported by the Office of Naval Research.

References:

1. H. Shirakawa, E. J. Louis, A. G. MacDiarmid, C. K. Chiang, and A. J. Heeger, Chem. Comm., 578 (1977)
2. C. K. Chiang, C. R. Fincher, Jr., Y. W. Park, A. J. Heeger, H. Shirakawa, E. J. Louis, S. C. Gau, and A. G. MacDiarmid, Phys. Rev. Lett. 39, 1098 (1977)
3. C. K. Chiang, M. A. Druy, S. C. Gau, A. J. Heeger, E. J. Louis, A. G. MacDiarmid, Y. W. Park, J. Am. Chem. Soc. 100, 1013 (1978)
4. S. C. Gau, A. G. MacDiarmid, C. K. Chiang, Y. W. Park and A. J. Heeger, to be published.
5. H. Shirakawa and S. Ikeda, Polym. J. 2, 231 (1971); H. Shirakawa, T. Ito, and S. Ikeda, Polym. J. 4, 460 (1973); T. Ito, H. Shirakawa, and S. Ikeda, J. Polym. Sci. Polym. Chem. Ed. 12, 11 (1974); T. Ito, H. Shirakawa, and S. Ikeda, J. Polym. Sci. Polym. Chem. Ed. 13, 1943 (1975).
6. S. L. Hsu, A. J. Signorelli, G. P. Pez and R. H. Baughman, J. Chem. Phys. (In press)
7. H. Shirakawa and S. Ikeda, (to be published).
8. Proceedings of the International Conference on Intercalation Compounds of Graphite, Mat. Sci. Engineering 31, (December 1977).
9. C. R. Fincher, D. L. Peebles, A. J. Heeger, M. Druy and A. G. MacDiarmid, to be published.

Figure Captions:


Figure 1: Electrical Conductivity (room temperature) as a function of dopant concentration:


Bromine	o o o
Iodine	• • •
AsF ₅	□ □ □


Figure 2: Compensation curve for Na-doped polyacetylene; conductivity ratio ($\sigma(t)/\sigma_{\text{initial}}$) vs. time. The sample was initially doped n-type and subsequently exposed to iodine vapor.


Figure 3: Compensation curve for Na-doped polyacetylene; conductivity ratio ($\sigma(t)/\sigma_{\text{initial}}$) vs. time. The sample was initially doped n-type and subsequently exposed to AsF₅ vapor.

Figure 4: I-V curve for a doped polyacetylene p-n junction.









TECHNICAL REPORT DISTRIBUTION LIST

<u>No. Copies</u>			<u>No. Copies</u>	
	Office of Naval Research Arlington, Virginia 22217 Attn: Code 472	2	Defense Documentation Center Building 5, Cameron Station Alexandria, Virginia 22314	12
	Office of Naval Research Arlington, Virginia 22217 Attn: Code 103A	6	U.S. Army Research Office P.O. Box 12211 Research Triangle Park, N.C. 27709 Attn: CRD-AA-IP	1
	ONR Branch Office 536 S. Clark Street Chicago, Illinois 60605 Attn: Dr. George Sandoz	1	Naval Ocean Systems Center San Diego, California 92152 Attn: Mr. Joe McCartney	1
	ONR Branch Office 715 Broadway New York, New York 10003 Attn: Scientific Dept.	1	Naval Weapons Center China Lake, California 93555 Attn: Head, Chemistry Division	1
	ONR Branch Office 1030 East Green Street Pasadena, California 91106 Attn: Dr. R. J. Marcus	1	Naval Civil Engineering Laboratory Port Hueneme, California 93041 Attn: Mr. W. S. Haynes	1
	ONR Branch Office 760 Market Street, Rm. 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	1	Professor O. Heinz Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
	ONR Branch Office 495 Summer Street Boston, Massachusetts 02210 Attn: Dr. L. H. Peebles	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
	Director, Naval Research Laboratory Washington, D.C. 20390 Attn: Code 6100	1	Office of Naval Research Arlington, Virginia 22217 Attn: Dr. Richard S. Miller	1
	The Asst. Secretary of the Navy (R&D) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1		
	Commander, Naval Air Systems Command Department of the Navy Washington, D.C. 20360 Attn: Code 310C (H. Rosenwasser)	1		

TECHNICAL REPORT DISTRIBUTION LIST

No. Copies

No. Copies

Dr. T. C. Williams
Union Carbide Corp.
Chemicals and Plastics
Tarrytown Technical Center
Tarrytown, New York 10591 1

Dr. R. Soulen
Contract Research Dept.
Pennwalt Corp. 1
900 First Avenue
King of Prussia, Pennsylvania 19406

Dr. A. G. MacDiarmid
University of Pennsylvania
Department of Chemistry
Philadelphia, Pennsylvania 19174 1

Dr. G. Dunks
Union Carbide Corp.
Corporate Research Laboratory
Tarrytown Technical Center
Tarrytown, New York 10591 1

Dr. A. Rheingold
SUNY Plattsburg
Department of Chemistry
Plattsburg, New York 12901 1

Dr. C. Pittman
University of Alabama
Department of Chemistry
University, Alabama 35486 1

Dr. H. Allcock 1
Pennsylvania State University
Department of Chemistry
University Park, Pennsylvania 16802

Dr. M. Kenney
Case-Western University
Department of Chemistry
Cleveland, Ohio 44106 1

Dr. R. Lenz
University of Massachusetts
Department of Chemistry
Amherst, Massachusetts 01002 1

Dr. M. David Curtis
University of Michigan
Department of Chemistry
Ann Arbor, Michigan 48105 1

Dr. M. Good
University of New Orleans
Department of Chemistry
Lakefront
New Orleans, Louisiana 70122 1

Douglas Aircraft Co.
3855 Lakewood Boulevard
Long Beach, California 90846
Attn: Technical Library
CI 290/36-84
AUTO-Sutton 1

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: Dr. T. T. Serafini, MS 49-1 1

Dr. J. Griffith
Naval Research Laboratory
Chemistry Section, Code 6120
Washington, D.C. 20375 1

Dr. G. Goodman
Globe-Union Inc.
5757 North Green Bay Avenue
Milwaukee, Wisconsin 53201 1

Dr. E. Fischer, Code 2853
Naval Ship Research and Development Ctr
Annapolis Division
Annapolis, Maryland 21402 1

Dr. Martin H. Kaufman, Head
Materials Research Branch (Code 4542)
Naval Weapons Center
China Lake, California 93555 1

Dr. J. Magill
University of Pittsburgh
Metallurgical and Materials Engineering
Pittsburgh, Pennsylvania 22230 /

Dr. C. Allen
University of Vermont
Department of Chemistry
Burlington, Vermont 05401 1

Dr. D. Bergbreiter
Texas A&M University
Department of Chemistry
College Station, Texas 77843 1